



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶: B41M 5/00	A1	(11) International Publication Number: WO 99/03685 (43) International Publication Date: 28 January 1999 (28.01.99)
(21) International Application Number: PCT/US98/14259 (22) International Filing Date: 8 July 1998 (08.07.98) (30) Priority Data: 08/892,902 14 July 1997 (14.07.97) US (71) Applicant: MINNESOTA MINING AND MANUFACTURING COMPANY [US/US]; 3M Center, P.O. Box 33427, Saint Paul, MN 55133-3427 (US). (72) Inventors: WALLER, Clinton, P., Jr.; P.O. Box 33427, Saint Paul, MN 55133-3427 (US). MROZINSKI, James, S.; P.O. Box 33427, Saint Paul, MN 55133-3427 (US). FAROOQ, Omar; P.O. Box 33427, Saint Paul, MN 55133-3427 (US). GRYSKA, Stefan, H.; P.O. Box 33427, Saint Paul, MN 55133-3427 (US). KLUN, Thomas, P.; P.O. Box 33427, Saint Paul, MN 55133-3427 (US). KREPSKI, Larry, R.; P.O. Box 33427, Saint Paul, MN 55133-3427 (US). (74) Agents: HORNICKEL, John, H. et al.; Minnesota Mining and Manufacturing Company, Office of Intellectual Property Counsel, P.O. Box 33427, Saint Paul, MN 55133-3427 (US).	(81) Designated States: AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CU, CZ, DE, DK, EE, ES, FI, GB, GE, GH, GM, HU, ID, IL, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, UA, UG, UZ, VN, YU, ZW, ARIPO patent (GH, GM, KE, LS, MW, SD, SZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG). Published <i>With international search report.</i>	
(54) Title: INK-JET PRINTABLE MICROPOROUS FILM (57) Abstract Ink-jet receptor media are disclosed that have both a fluid management system and a pigment management system for use with pigmented ink-jet inks that produce vibrant, durable images. The fluid management system is provided by microporous media with the presence of surfactants, if needed. The pigment management system is provided by either fluorinated silica particles or inorganic multivalent metal salts impregnated into pores of the microporous media. Methods of making and using are also disclosed.		

BEST AVAILABLE COPY

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece			TR	Turkey
BG	Bulgaria	HU	Hungary	ML	Mali	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MN	Mongolia	UA	Ukraine
BR	Brazil	IL	Israel	MR	Mauritania	UG	Uganda
BY	Belarus	IS	Iceland	MW	Malawi	US	United States of America
CA	Canada	IT	Italy	MX	Mexico	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NE	Niger	VN	Viet Nam
CG	Congo	KE	Kenya	NL	Netherlands	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NO	Norway	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	NZ	New Zealand		
CM	Cameroon			PL	Poland		
CN	China	KR	Republic of Korea	PT	Portugal		
CU	Cuba	KZ	Kazakhstan	RO	Romania		
CZ	Czech Republic	LC	Saint Lucia	RU	Russian Federation		
DE	Germany	LI	Liechtenstein	SD	Sudan		
DK	Denmark	LK	Sri Lanka	SE	Sweden		
EE	Estonia	LR	Liberia	SG	Singapore		

BEST AVAILABLE COPY

INK-JET PRINTABLE MICROPOROUS FILM

5

Field of Invention

This invention relates to a microporous inkjet receptor that provides excellent images with pigmented inks deposited thereon.

10

Background of Invention

15

Inkjet imaging techniques have become vastly popular in commercial and consumer applications. The ability to use a personal computer and desktop printer to print a color image on paper or other receptor media has extended from dye-based inks to pigment-based inks. The latter provide brilliant colors and more durable images because pigment particles are contained in a dispersion before being dispensed using a thermal inkjet print head, such as those commercially available from Hewlett Packard Corporation or LexMark Corporation in inkjet printers commercially available from Hewlett Packard Corporation, Encad Inc., Mimaki Corporation, and others.

20

25

Ink jet printers have been in general use for wide-format electronic printing for applications such as, engineering and architectural drawings. Because of the simplicity of operation, economy of ink jet printers, and improvements in ink technology the inkjet imaging process holds a superior growth potential promise for the printing industry to produce wide format, image on demand, presentation quality durable graphics.

30

The components of an ink jet system used for making graphics can be grouped into three major categories:

- 1 Computer, software, printer.
- 2 Ink.
- 3 Receptor sheet.

The computer, software, and printer will control the size, number and placement of the ink droplets and will transport the receptor film. The ink will contain the colorant or pigments which form the image and the receptor film provides the medium which accepts and holds the ink. The quality of the ink jet image is a function of the total system. However, the composition and interaction
5 between the ink and receptor film is most important in an ink jet system.

Image quality is what the viewing public and paying customers will want and demand to see. Many other demands are also placed on the ink jet media/ink system from the print shop, such as rapid drying, humidity insensitivity,
10 waterfastness and overall handleability. Also, exposure to the environment can place additional demands on the media and ink (depending on the application of the graphic).

Porous film is a natural choice to use as a ink jet receptive media because the capillary action of the porous film can wick the ink into the pores much faster
15 than the absorption mechanism of film forming water soluble coatings. However, in the past, when a porous coating or film has been employed to achieve desired quick dry, optical density has suffered greatly because the colorant penetrates too deep into the porous network. This type of problem is magnified by printers that dispense high volumes of ink per drop because extra film thickness may be
20 required to hold all the ink. When the pore size and pore volume of the membrane is opened to allow the pigments to penetrate, the pigments can be stratified in the membrane. Meaning, the black, cyan, magenta, and yellow will be predominately found at different depths depending on order of application. Furthermore, lateral
25 diffusion of the ink can also be a problem inherent in porous membranes used as receptive media. Hence, some of the first color(s) applied is /are optically trapped in the image by subsequent application of other pigmented ink. When pigmented inks are jetted onto a porous film that has a pore size that is too small, color pigments will be filtered on the top of the membrane rendering high image density,
30 but the pigments will easily smear and have the effect of never drying. Also, excess fluid from the ink can pool and run on the image before the water/glycol carrier is wicked away.

BEST AVAILABLE COPY

The chemical formulation of the pigmented inkjet ink has considerable complexity due to the requirement of continued dispersion of the pigment particles in the remainder of the ink.

The typical consumer medium for receiving dye-based inkjet inks has been paper or specially coated papers. However, with too much inkjet ink in a given area of the paper, one can see the over-saturation of the paper with the aqueous ink in which dye was dissolved.

As inkjet inks have become more commercially oriented and pigmented-based inks have become more prevalent, different media have been tried in an attempt to control the management of fluids in the ink. One effort combines a hygroscopic layer to manage fluids in the ink with a hydrophilic layer thereon, upon which the ink can be deposited. Pigment particles remain with the hydrophilic layer while fluids pass through to the hygroscopic layer for rapid drying.

Ink receptive element containing absorptive polymers and polymer particles together with a binder has been disclosed in U.S. Pat No. 5,084,340.

U.S. Pat No. 4,781,985 discloses an inkjet transparency film comprising a substantially transparent resinous support containing a clear absorptive coating thereon.

U.S. Pat No. 5,102,731 mentioned the use of a non-porous substrate and a coating layer formed thereon comprising a carboxyl group-containing ionomeric hydrophilic urethane resin and organic and/or inorganic fine particles.

U.S. Pat No. 4,954,395 discloses a recording medium which comprises a porous ink-transporting layer and a nonporous ink-retaining layer.

German Patent No. 30 24 205 uses a pigment/binder mixture on the ink receiving paper. The purpose of the pigment is to add whiteness and porosity. A high pigment load leads the film to high porosity. This makes the paper smudge proof but this has a negative effect on optical density, because the dyes in the ink are drawn into the interior of the material.

BEST AVAILABLE COPY

Japanese Patent JP 61-041585 discloses a method for producing printing material using a ratio of PVA/PVP. The disadvantage is inadequate waterfastness and wet rub off properties.

Japanese Patent JP61-261089 discloses a transparent material with cationic conductive resin in addition to a mixture of PVA/PVP. The material is water fast and smudge proof but the wet rub off properties are poor.

US Pat. No. 5,569,529 discloses a coating with PVP/PVA with water soluble compounds containing aldehyde groups. They also added quaternary ammonium compounds such as polydiallyldimethylammonium chloride. Plus on the backside of the paper they coat on hydrophilic colloidal binders such as starch, PVA, or oxidized potato starch. Some color density is lost when submerged in water but after the initial loss it is resistant to further color loss by a weak rubbing test.

European Patent Publication EP 0 716 931 A1 discloses a system using a dye capable of co-ordinate bonding with a metal ion in two or more positions. Again binder resins are used with inorganic pigments in the paper or film. The metal ion was preferred to be jetted on before imaging and additional heating is necessary to complete the reaction. This system was not claiming to be water fast, the focus is long term storage without fading from heat or light.

U.S. Pat. No. 4,419,388 discloses a waterproofing system where after imaging one sprays on a compound containing a mono-valent metal atom or ammonium group with a tri-valent metal atom. An example of these compounds claimed are $\text{KAl}(\text{SO}_4)_2 \cdot 12 \text{H}_2\text{O}$. Claim 8 discloses aluminum sulfate can be applied to the paper before imaging, but the mono-valent component then has to be in the ink.

U.S. Pat. No. 5,537,137 discloses a system to achieve waterfastness by curing with heat or UV light. In the body of the patent, examples of their coatings contained Ca^{++} from CaCl_2 . This was added to provide reactive species for the acid groups on the dispersed polymer. The coating remains water soluble until UV or heat curing after imaging.

BEST AVAILABLE COPY

U.S. Pat. No. 4,649,064 uses multivalent metal salts in a gelatin coating to cross-link inks that contain polyesteramide with sulfonate function groups. The ink receiving layer is cross linked with bis(vinylsulfonylmethyl)ether. Careful selection of materials is required because the metal salts are capable of cross-linking the gelatin coating before the ink is applied.

U.S. Pat. No. 4,732,786 This patent also uses an insolubilized hydrophilic polymer (gelatin) with polyvalent cations from metallic salts and claims advantages with their methods because they can make the coating with a low pigment/binder ratio.

U.S. Pat. No. 5,429,860 discloses an ink/ receptor system that may contain multivalent cations. This system is UV activated after imaging to crosslink the materials.

Hence, the current special ink jet media employ vehicle absorptive components, and sometimes optional additives to bind the inks to the media. As a consequence current media are inherently moisture sensitive and can be fragile to handling and subject to finger smearing. Moreover, the vehicle absorptive components usually consist of water soluble (or swelling) polymers which result in slower printing speeds and dry times.

Pigmented ink delivery systems have also dealt with pigment management systems, wherein the resting location of the pigment particles are managed to provide the best possible image graphic. For example, PCT Publication WO96/08377 discloses a pigment management system in which a suitable supporting layer (including in a listing a microporous layer) has a two layer fluid management system: a protective penetrant layer and a receptor layer, both layers containing filler particles to provide two different types of protrusions from the uppermost protective penetrant layer. Electron microphotographs in that application show how the pigment particles of the ink encounter smooth protrusions that provide a suitable topography for pigment particle "nesting" and rocky protrusions that assist in media handling and the like.

Other ink receptors have been disclosed, including U.S. Pat. Nos. 5,342,688 (Kitchin); 5,389,723 and 4,935,307 (both Iqbal et al.); 5,208,092 (Iqbal)

5,302,437 (Idei et al); U.S. Pat. No. 5,206,071 (Atherton et al.); and EPO Patent Publication 0 484 016 A1.

Summary of Invention

5 While each of the fluid management systems and each of the pigment management systems of the above prior efforts are suitable for the uses intended, none of these prior disclosures recognizes the need for an inkjet receptor that has both a pigment management system for flocculating or agglomerating incoming ink and a fluid management system for efficiently dispensing with the carrier fluids
10 within a porous substrate.

What is needed is new technology to permit the use of porous membranes that will achieve high quality imaged graphics with quick drying without water soluble/swellable polymers, or additional processing, or the current porous film drawbacks discussed above. Another need in the art is the ability to tailor a
15 microporous medium based on the ink used and the printer configurations.

Furthermore, no two inks are exactly alike in formulation and no clear printer configuration standard has emerged. This variability in the marketplace requires adjustment in the remaining element of the ink jet printing system that is
20 in control of the user, the receptor medium employed.

While Warner et al. above discloses the use of a microporous medium as the supporting layer, Warner et al. provide their fluid management system using two coating layers. The art needs a microporous receptor that does not require coating layers on a major surface of the receptor yet provides both pigment and
25 fluid management systems.

One aspect of the present invention is an inkjet receptor medium, comprising a porous substrate having a fluid management system and having a pigment management system in contact with surfaces of pores of the substrate therein.

30 Another aspect of the invention is an inkjet receptor comprising a microporous membrane impregnated with an inorganic multivalent metal salt

together with a surfactant or combination of surfactants chosen for the ink and membrane being employed.

Another aspect of the present invention is an inkjet receptor comprising a microporous membrane impregnated with a microporous fluorinated silica agglomerate together with a binder and a surfactant or a combination of surfactants
5 for the ink and membrane being employed.

Another aspect of the present invention is an inkjet receptor comprising a microporous membrane impregnated with a microporous fluorinated silica agglomerate together with a binder and a surfactant or combination of surfactants
10 wherein the said surfactants are selected from the group of hydrocarbon-based anionic surfactants, silicon-based non-ionic surfactants or fluorocarbon-based non-ionic based surfactants or a combination thereof.

The novel receptors, when imaged in an inkjet printer, provide very high density and very high quality images which are tack-free and instantaneously dry
15 to touch.

Another aspect of the present invention is an impregnation for a porous media/ink set, making possible high speed production of high quality graphic images for current and future ink jet technologies. The imbibed porous substrate provides improved durability, waterfastness, smear resistance, effective quick dry
20 times, and long term durability using porous film without absorptive polymeric binders, or additional process such as UV exposure or heating. Accordingly, the invention provides a media/ink set comprising: a microporous membrane that bears a surface modifier impregnating therein, containing wetting surfactant(s) and a
25 water soluble multivalent metal salt(s), and an ink that contains pigment colorants.

In a preferred embodiment, the ink colorant is a pigment dispersion having a dispersant that binds to the pigment that will destabilize, flocculate, agglomerate, or coagulate the pigments on contact with the media component. Depositing each of colors at or just below the surface of the membrane allowing the carrier fluid to
30 wick into the membrane where the fluid management system can take over while providing a sheltered location for the pigments as managed by the colorant management system.

Also preferred for the receptive media is a Thermally Induced Phase Separated (T.I.P.S.) microporous membrane disclosed in U.S. Pat. No. 4,539,256 (Shipman) and available from 3M. For optimization, the pore size and pore volume of the porous film can be adjusted for the model or make of the ink jet printer to correctly hold the volume of ink dispensed by the printer ensuring the highest possible image quality. The coating on the preferred media/ink set has special utility in the demanding ink jet printing applications found in commercial printing.

A feature of the present invention is the ability to "fine tune" the properties of receptors of the present invention to deal with the variables of inkjet ink delivery, including without limitation: drop volume, porosity of media, and capacity of media to receive ink.

Another feature of the present invention is that it allows the use of complex porosity in a porous material that provides both a tortuous path for fluid management and a tortuous path that ensnares the pigment initially and continually during ink delivery. A variety of presently commercially microporous media that have tortuous paths become useful when completed according the methods of the present invention which is a major limitation of the teachings of U.S. Pat. No. 5,374,475 (Watchli et al).

Another feature of the present invention is the ability to use the present invention for very rapid printing of brilliant, pigmented inkjet inks that dry rapidly as well.

Another feature is satisfaction of many goals of inkjet printing: is competitive in cost; works with pigmented inks; has high resolution; has high color density; has a wide color gamut; is waterfast; is smudge resistant; uses capillary action of the porous membrane for rapid fluid absorption (effective quick dry); does not show banding or coalescence; doesn't show finger prints when handled before or after printing; is a brighter white that does not yellow in time; is stable during temperature and humidity swings; is very outdoor durable with or without an overlamine; has long shelf life; and is superior when backlighting is used.

An advantage of the present invention is ease of manufacture of microporous receptors without topcoats.

Another advantage of the present invention is the images look excellent for reflective or backlit viewing without heat collapsing the porous substrate as is necessary according to U.S. Pat. No. 5,374,475 (Walchli et al.)

Another advantage of the present invention is very fast-drying of the impregnated salt or microporous silica/surfactant system during coating. The process helps save significant amounts of energy.

Optional additives such as stabilizers, ultraviolet light absorbers, anti-oxidants, mold inhibitors, dye mordants, binders, or polymers can be introduced into the receptors of the present invention so long as they do not interfere with the pigment or fluid management systems.

Optional additional layers can reside on a major surface designated for imaging, such as overlaminates and clear coatings that protect the image graphic. Alternatively, optional additional layers can reside on a major surface opposing the imaging surface, such as stronger layers for laminate construction or adhesive layers for adhesion of the image graphic to an installation surface, either permanently or temporarily. A release liner can be used to protect the adhesive layer during imaging and storage.

Other features and advantages will become identified in discussing embodiments of the invention.

Embodiments of Invention

Microporous Substrates

Porous substrates useful in the present invention include symmetrical membranes, asymmetrical membranes, and porous films also known as skinned membranes. Symmetrical membranes have porosity on opposing major surfaces of approximately the same pore size. Asymmetrical membranes have porosity on opposing major surfaces that are not of similar pore sizes. A skinned membrane has considerable porosity on one major surface but essentially no porosity on the opposing major surfaces.

Nonlimiting examples of commercially available microporous membranes include: nylon and polysulfone membranes from Gelman Sciences, Ann Arbor Michigan; polyolefin membranes from Amoco Corp., Chicago Ill.; and polyolefin, nylon, or ethylene vinyl alcohol membranes from 3M.

5 A suitable microporous membrane for printing on a 100-140 picoliter per drop size for each color and 300 x 300 drops per inch printer has a thickness or caliper ranging from about 75 μm to about 200 μm , and preferably from about 100 μm to about 175 μm . It is a reality of ink jet printing that as many as four pigment drops, representing each of the four printing colors, are landing on a single spot of
10 the ink jet receptor medium in order to generate any one of the myriad of colors available in ink jet printing.

The microporous membrane can have a porosity value as calculated by measuring the bulk density of the membrane in grams/cm^3 from the specific gravity measurement determined according to ASTM-D-792-66 and substituting that value
15 into the following formula:

$$100 \times [1 - \text{measured density/polymer density}] = \text{porosity},$$

ranging from 20 to about 95 and preferably from about 30 to about 50.

20 Alternatively, the membrane can have a pore volume ranging from about 80 to about 100% of the anticipated ink volume dispensed from a given inkjet printer.

Bubble point is a measurement of the largest effective pore size in a symmetrical membrane that has through-porosity, as measured according to ASTM F-316, and can range from about 0.20 μm to about 2.0 μm and preferably about
25 0.40 μm to about 0.80 μm .

Surface energy of the porous substrate before treating with the pigment and fluid management systems can range from 20 to 70 dynes/cm as defined in the Third Edition of the POLYMER HANDBOOK by J. Brandrup and E.H. Immergut (1989).

30 Microporous membranes can be of unlimited length, depending on the size of the roll that can be facilely handled. Usually, commercial quantities of the

microporous membrane for feeding into a commercial printer can be a roll having a length in excess of 10 meters, and preferably in excess of 20 meters.

As inkjet media become more useful with wide format inkjet printers, the width of the microporous membrane becomes important from a perspective of imaging productivity and convenient graphic installation. The membrane can have a width ranging from about 0.25 meters to about 2 meters and preferably a width ranging from about 0.60 meters to about 1.2 meters.

A particularly preferred microporous membrane for the present invention when printing with a 140 picoliter/drop x 4 colors x 300 x 300 drops/inch is a polypropylene membrane prepared using thermally induced phase separation techniques according the disclosures of U.S. Pat. Nos. 4,539,256 (Shipman et al.), 4,726,989 (Mrozinski), and more particularly 5,120,594 (Mrozinski). This membrane has the following properties:

15	Bubble point	- 0.65 μ m
	Gurley 50cc	20 sec
	Porosity % void	45 %
	Surface wetting Energy (before treatment)	30 dynes/cm ²
20	Caliper	0.178 mm (7 mil)

Fluid Management System

The porosity, Gurley resistance to air flow, pore volume, surface energy, and caliper of the microporous membrane can be selected to provide suitable fluid management for the image graphic. Therefore, depending upon the pigmented ink selected for imaging, the type of ink can determine the type of porous surface most suitable for wicking of fluid from the deposited image graphic into the pore volume of the membrane. Sometimes, the chemical and physical properties of the porous surface requires assistance from surfactants or hydrophilic polymers to aid in the management of ink fluids.

Therefore, a variety of surfactants or polymers can be chosen to provide particularly suitable surfaces for the particular fluid components of the pigmented

inkjet inks. Surfactants can be cationic, anionic, nonionic, or zwitterionic. Many of each type of surfactant are widely available to one skilled in the art. Accordingly, any surfactant or combination of surfactants or polymer(s) that will render said substrate hydrophilic and can be employed.

5 These surfactants can be imbibed into porous surfaces of the membrane. Various types of surfactants have been used in the coating developed systems. These may include but are not limited to fluorochemical, silicon and hydrocarbon-based ones wherein the said surfactants may be anionic or non-ionic. Furthermore, the non-ionic surfactant may be used either -as it is or in combination with another
10 anionic surfactant in an organic solvent or in a mixture of water and organic solvent, the said organic solvents being selected from the group of alcohol, amide, ketone and the like.

 Various types of non-ionic surfactants can be used, including but not limited to: Dupont's Zonyl fluorocarbons (e.g., Zonyl FSO); 3M's FC- 1 70 or 171
15 surfactants; BASF's (Pluronic) block copolymers of ethylene and propylene oxide to an ethylene glycol base; ICI's (Tween) polyoxyethylene sorbitan fatty acid esters; Rohm and Haas's (Triton X series) octylphenoxy polyethoxy ethanol ; Air Products and Chemicals, Inc. (Surfynol) tetramethyl decynediol; and Union
20 Carbide's Silwet L-7614 and L-7607 silicon surfactants and the like known to those skilled in the art.

 Various types of hydrocarbon-based anionic surfactants can also be used, including but not limited to: American Cyanamid's (Arerosol OT) surfactants like dioctylsulfosuccinate-Na-salt or dialkylsulfosuccinate-Na-salt.

25 Various types of cationic surfactants can also be used, including but not limited to: benzalkonium chloride, a typical quaternary ammonium salt.

Pigment Management System

30 The microporous material has a pigment management system based on addition of materials into the pore volume of the porous substrate.

Two embodiments are disclosed for the Pigment Management System:
Silica Agglomerates and Multivalent Metal Salts. There are benefits of both and
some distinctions that can be employed by those skilled in the art to advantage.

Both embodiments provide a quick dry, high color density, high resolution
5 image that is smudge resistant (if the silica agglomerates reside below the exposed
surface of the receptor medium).

The silica agglomerate embodiment works with both dye-based and
pigment-based inks, whereas the metal salt embodiment works better with
pigment-based inks.

10 The silica agglomerate is not soluble in water either for preparing imbibing
solutions or after imaging. The metal salt is soluble in water for both preparing
solutions and during imaging, but not after complexing with the dispersing aid that
surrounds the pigment particles in the ink.

15 The silica agglomerate is composed of particles trapped inside the porous
receptor medium, whereas the metal salt is composed of coatings on the interior
surfaces of the porous receptor medium.

The silica agglomerate is believed to serve as a chemical trap, a
functionalized silica, of ink passing through the interior pores interacting with
dispersants that surround pigment particles, leaving the colorant with the
20 agglomerate, providing a chemical means of pigment management based on
particulates within the pores. The metal salt is believed to serve as reagents to
rapidly destabilize dispersants surrounding the pigment particles in the ink,
whereby the pigment particles coagulate or flocculate as the remainder of the ink
25 fluid continues through pores and along the surfaces of the receptor medium. The
multivalent salts therefore provide a chemical means of pigment management
along surfaces of the pores.

The former requires penetration into the porous receptor medium to
minimize physical removal from the medium. The latter coats surfaces of the
30 receptor medium and, once dried, is resistant to physical removal.

One way to qualify various pigment management systems is to place a
quantity of the targeted ink into a solution of a pigment management system. A




non-particulate chemical acting as in pigment management will flocculate and separate the pigment particles from the ink, rapidly separating the appearance of the experimental liquid into two layers, whereas a particulate chemical acting pigment management will not separate rapidly the experimental liquid into two layers.

While two embodiments are described in more detail below, one skilled in the art can also employ other compositions to provide either primarily physical or primarily chemical means of pigment management without departing from the scope of the present invention.

Silica Agglomerates

One embodiment of the pigment management system used in the present invention relies on fluorinated silica agglomerates filling at least a significant portion of the pore volume of the microporous material. The silica-agglomerates are hydrophobic and are sympathetic with pigment particles dispersed within a pigmented ink.

The preparation of fluorinated silica particles can be represented by the following equation:



The size of the silica particles can range from about 0.1 to about 50 μm and preferably from about 1 to about 10 μm .

The amount of the silica particles can range from about 2 to about 20 weight percent and preferably from about 3 to about 10 weight percent.

Impregnation of the silica particles into the pore volume of the microporous membrane requires the particles not to be oversized and operates according to the discussion above.

One advantage of functionalized silica particles discussed above is their microporosity which can aid in the physical interaction of pigment particles in ink moving through the pores of the substrate. A more important advantage is their functionalized surfaces for interaction with dispersants engaged with those pigment particles.

10 Multivalent Metal Salts

A second embodiment of the pigment management system relies on an inorganic multivalent metal salt or salts to control the reception of pigment particles onto the porous surfaces of the receptor.

Nonlimiting examples of inorganic multivalent metal salts useful in the present invention include the metal cations from Group 11 and above in the Periodic Table, such as Ca, Mg, Ti, Zr, Fe, Cu, Zn, Ta, Al, Ga, Sn, with counter ions such as sulfate, nitrate, acetate, propionate and the like.

Other examples of multivalent metal salts depend on and operate within the conditions of solubility rule concerning the dissolving of salts in water, (General Chemistry Principles and Structure 5th edition p. 132). These rules have hierarchy, meaning if there is conflict with a rule, the preceding rule takes precedence. For example, rule 8 states all carbonates (CO_3^{2-}) are insoluble in water. The exceptions to this rule are found when following rules 1 and 2, which is all salts of the alkali metals and all salts of the ammonium (NH_4^+) ion are soluble. To employ these rules means that the ammonium and the alkali metal salts do not flocculate ink on contact when imbibed in the porous membrane. Therefore, the salts formed by the carbonate ion are not as useful as other counter ions. As another example, the salt, NaCl, does not flocculate the ink as it contains only the +1 cation (sodium) found in Group 1A of the Periodic Table. The salt, CaCl_2 , does flocculate the ink as the +2 (calcium) is found in Group IIA.

Specific examples of preferred salts include aluminum sulfate, aluminum nitrate, gallium nitrate, ferrous sulfate, chromium sulfate, calcium propionate, zinc sulfate, zinc acetate, zinc chloride, calcium chloride, calcium bromide, magnesium sulfate, magnesium chloride, and combinations thereof. These compounds are typically sold and can be used in the hydrated form. Of the various possible salts, aluminum sulfate is presently preferred.

The amount of salts that can be used in the coating solution for imbibing in the porous substrate of the present invention can range from about 0.5 wt % to about 50.0 wt %, and preferably from about 1.0 wt % to about 10.0 wt %.

Optional Additives

Stabilizers

Optionally, heat or ultraviolet light stabilizers can be used in receptors of the present invention. Nonlimiting examples of such additives include Ciba-Geigy's Tinuvin 123 or 622LD, or Chimassorb 944 (hindered amine light stabilizers), and BASF's Uvinul 3008. Such stabilizers can be present in a coating solution to be impregnated into the membrane in the range from about 0.20 weight percent to about 20.0 weight percent. Preferably, the stabilizer is present in an amount from about 1.0 to about 10.0 wt %.

Absorbers

Optionally, ultraviolet light absorbers can be used in receptors of the present invention. Nonlimiting examples of such absorbers include Ciba-Geigy's Tinuvin II 30 or 326, BASF's tvinul 40501 1, and Sandoz Chemiciii Corp.'s Sanduvor VSU or 3035. Such absorbers can be present in the coating solution and can range from about 0.20 weight percent to about 20.0 weight percent. Preferably, the absorber is present in an amount from about 1.0 to about 10.0 wt

Anti-Oxidants

Optionally, anti-oxidants can be used in receptors of the present invention. Nonlimiting examples of such anti-oxidants include Ciba-Geigy's Irganox 1010 or 1076, BASF's Uvinul 2003 AD, and Uniroyal Chemical's. Such anti-oxidants can

be present in the coating solution and can range from about 0.20 weight percent to about 20.0 weight percent. Preferably, the anti-oxidant is present in an amount from about 0.40 to about 10.0 wt %.

5 Optional Additional Layers

While a receptor of the present invention has two major opposing surfaces and can be employed for inkjet reception on both surfaces, more likely but optionally, one of the major surfaces can be dedicated for the purpose of adhering the finished image graphic to a supporting surface such as a wall, a floor, or a
10 ceiling of a building, a sidewall of a truck, a billboard, or any other location where an excellent quality image graphic can be displayed for education, entertainment, or information.

Minnesota Mining and Manufacturing Company (3M) offers a variety of image graphic receptor media and has developed an array of pressure sensitive
15 adhesive formulations that can be employed on the major surface opposing the surface intended for imaging. Among these adhesives are those disclosed in U.S. Pat. Nos. 5,141,790 (Calhoun et al.); 5,229,207 (Paquette et al.); 5,296,277 (Wilson et al.); 5,362,516 (Wilson et al.); EPO Pat. Pub. EP 0 570 515 B I
20 (Steelman et al.), and PCT Publications WO 97/31076 WO 97/31077.

Any of these adhesive surfaces should be protected by a release or storage liner such as those commercially available from Rexam Release of Oakbrook, Illinois USA.

Alternatively to adhesives, mechanical fasteners can be used if laminated in
25 some known manner to that opposing major surface of the receptor of the present invention. Nonlimiting examples of mechanical fasteners include hook and loop, Velcro™, Scotchmate™ and Dual Lock™ fastening system.

While the imaging major surface is not covered before imaging, after
30 imaging, the invention can benefit from an optional layer applied to that imaged major surface to protect and enhance the image quality of the image on the receptor. Nonlimiting examples of optional layers are overlaminates and protective clear coatings commercially available from Minnesota Mining and Manufacturing

Company (3M) from its Commercial Graphics Division and those disclosed in U.S. Pat. No. 5,681,660 (Bull et al). Other products known to those skilled in the art can also be used.

5 Method of Making the Invention

The invention in its preferred mode is made by first making the microporous substrate using the techniques of TIPS disclosed in Shipman et al or either Mrozinski patent identified above, followed by impregnation of surfactants, as needed, and the pigment management system of multivalent metal salts or silica
10 agglomerates or others. After the receptor is prepared, it can be imaged using conventional thermal ink jet imaging techniques embodied in commercially available printers.

Optional steps after imaging include a fusing of the imaged media according to the teachings of U.S. Pat. No. 5,443,727 (Gagnon) or a backfilling of
15 the remaining pore volume with any material having an index of refraction that is similar to the index of refraction of the imaged receptor of the present invention. Nonlimiting examples of such backfilling materials include waxes, glycols, oils, alkyds, urethanes, acrylics, and the like. Preferably, for greater structural integrity,
20 one can crosslink these backfilling materials using techniques known to those skilled in the art.

Impregnation of the salt or silica can be accomplished in any of the following manners:

Silica agglomerate can be prepared by reacting a colloidal silica sol
25 (average particle size ~ 4 nm) in a three-neck flask fitted with a reflux condenser and a mechanical stirrer with isopropylamine or quinuclidine under stirring at room temperature, followed by adding dropwise to the mixture, at room temperature, diluted hydrofluoric acid under stirring. After the addition of all the acid, the
30 system can be heated to vigorous refluxing of water under moderate mechanical stirring for more than a day. After this period of time an opaque colloidal dispersion results, which can be combined with surfactants and binder. Impregnation of the dispersion can be carried out into the porous substrate by

conventional coating techniques, such as a slot fed knife, rotogravure devices, padding operations, dipping, spraying, etc.

For the metal salt embodiment, the salt/surfactant(s) are dissolved or mixed in a mixture of de-ionized water and an alcohol. Impregnation or imbibing of the solution is done with conventional coating equipment like a slot fed knife, rotogravure devices, padding operations, dipping, spraying, etc. It is preferred that the coating composition fill the pores of the substrate without leaving substantial quantities on the surface. Excessive amounts of high solids coatings could plug the pores as the water/alcohol evaporate which in turn causes smearing and slow dry times during inkjet printing.

Optional additives can be added before, during, or after the impregnation of the pigment management system.

Before or after the principal receptor is prepared, optional adhesive or mechanical fastener laminates can be added using commercially acceptable coating or extrusion techniques.

Usefulness of the Invention

Inks

The printing industry has previously employed dye-based inks, although pigment-based inks are becoming more prevalent. Use of pigment colorants is preferred over dye colorants because of durability and ultraviolet light stability in outdoor applications.

Further, reference to inks with respect to this invention concerns aqueous-based inks, not solvent-based inks. Aqueous-based inks are currently preferred in the printing industry for environmental and health reasons, among other reasons.

Minnesota Mining and Manufacturing Company (3M) produces a number of excellent pigmented inkjet inks for thermal inkjet printers. Among these products are Series 8551; 8552; 8553; and 8554 pigmented inkjet inks. The use of four principal colors: cyan, magenta, yellow, and black permit the formation of as many as 256 colors or more in the digital image. Further, pigmented inkjet inks, and components for them, are also produced by others, including Hewlett Packard,

DuPont, and a number of other companies that can be located at many commercial trade shows dedicated to the imaging and signage industries.

Image Graphics

5 The receptor of the present invention is a highly fluid absorptive inkjet medium. The porous receptor is opaque because of its inherent light scattering ability. Using clear backing support, the receptor can be used for either reflective or backlit applications.

10 When the receptor material of this invention is imaged in Encad Novajet wide-format printers with high drop volume, it results in images with excellent quality with high color density which instantaneously dry to touch or any other dry tests. Briefly, but not being limited by a particular theory, the presence of the salt impregnated into pores provides instantaneous capturing of the pigment particles just below the surface of the porous receptor and controls the depth the pigment particles go to by destabilizing, flocculating, agglomerating, or coagulating them
15 from their suspension/dispersion in the ink.

Further embodiments and their unexpected advantages over the art are described in the following examples.

Examples

20 Unless otherwise stated, all examples use an oil-in microporous polypropylene film made according to the teachings of U.S. Pat. No. 5,120,594 with the following pore properties: 175 μm thick; a pore size of 0.65 μm ; Gurley resistance to air flow of 20 seconds to pass 50 cc through 2.54 cm^2 ; and 40 - 42 % porosity. The porous film was attached to a 125 μm thick paper liner using 3M
25 adhesive disclosed in EPO Pat. Pub. EP 0 570 515 B1 (Steelman et al.) (with 50 parts of aqueous pressure sensitive adhesive and 43.5 parts of adhesive microspheres) to allow it to travel smoothly through an Encad Nova Jet III printer fitted with 140 picoliter/drop HP 51626 cartridges filled with 3M pigmented inks.

30 The first four examples describing the receptor media of the invention were impregnated with a UV and thermal stabilizing coating solution before the pigment/fluid management solution was applied. Both solutions were flood coated

on the porous film and wiped with a # 4 Meyer rod. The film was dried at ambient conditions. The stabilizing solution could also be applied after the receptor coating.

5

UV and thermal stabilizer composition:

	Tinuvin- 1 13 0	2%
	Tinuvin- 123	3.5%
	Irganox-1010	0.4%
10	Acetone	1%
	Ethanol	93.1 %

Example- 1:

This example shows a receptor composition consisting of a single
 15 multivalent metal salt and a mixture of a non-ionic fluorochemical and an anionic hydrocarbon-based surfactants flood-coated with a Meyer rod #4 onto the oil-in-PP porous film. The film was dried in air at ambient conditions. After printing, the receptor was dry to the touch and had excellent image quality. Color density measurements are listed in Table 1. The measurements were taken with a Gretag
 20 SPM-50 calorimeter in reflectance mode set at:

Illumination D65
 Observation angle 20
 Density Standard DIN
 25 White base Abs
 Filter none

Receptor Composition I

	Aluminum sulfate	5.0 wt %
30	Zonyl-FSO (fluorochemical surfactant, Dupont)	1.0 wt %
	Diocylsulfosuccinate-Na-salt (hydrocarbon surf,	Cyanamid) 1.0 wt %
	Isopropyl Alcohol	15 wt %
	Ethyl Alcohol	10 wt %

De-ionized water

68 wt %

Example-2

- 5 This example shows a composition consisting of a single multivalent metal salt and a mixture of a non-ionic fluorochemical and an anionic hydrocarbon-based surfactant flood-coated onto the oil-in-PP porous film with a Meyer rod #4. The film was dried in air at ambient conditions. After printing the receptor was dry to the touch and had excellent image quality. Color density values are listed in Table
- 10 1.

Composition-II :

	Aluminum sulfate	5.0 wt %
	FC-170C (fluorochemical surfactant, 3M)	1.0 wt %
15	Dioctylsulfosuccinate-Na-salt	1.0 wt %
	Isopropyl Alcohol	15 wt %
	Ethyl Alcohol	10 wt %
	De-ionized water	68 wt %

20

Example-3

- This example shows a composition consisting of a single multivalent metal salt and a mixture of a non-ionic silicon-based surfactant e.g., a Silwet L- 7687 compound and an anionic hydrocarbon-based surfactant flood coated onto the oil-
- 25 in PP porous film with a Meyer rold #4. The film was dried in air at ambient conditions After printing the receptor was dry to the touch and had excellent image quality. Color density measurements are in Table 1.

Composition-III

30	Aluminum sulfate	5.0 wt %
	Silwet L-7607 (Silicon surfactant, Union Carbide)	1.0 wt %
	Dioctylsulfosuccinate-Na-salt (hydrocarbon surf, Cynamid)	1.0 wt %

Isopropyl Alcohol	15 wt %
Ethyl Alcohol	10 wt %
De-ionized water	68 wt %

5 Example-4

This example shows a composition consisting of a mixture of binary metal salts and a fluorochemical and hydrocarbon-based surfactants flood-coated onto the oil-in-PP porous film with a Meyer rod #4. The film was dried in air at ambient conditions. After printing the receptor was dry to the touch and had excellent image quality. Color density measurements are in Table 1.

Composition-IV:

Potassium-Aluminum sulfate	1.66 wt %
Ammonium-Aluminum sulfate	1.67 wt %
15 Ferrous-Aluminum sulfate	1.67 wt %
Zonyl-FSO -(fluorochemical surfactant)	1.0 wt %
Diocylsulfosuccinate (hydrocarbon surf, Cyanamid)	1.0 wt %
Isopropyl Alcohol	25 wt %
20 De-ionized water	68 wt %

TABLE 1
COLOR DENSITY MEASUREMENTS

Composition	Color Density						
	Black	Cyan	Magenta	Yellow	Red	Green	Blue
II (unlaminated)	1.26	1.24	1.11	1.14	1.16	1.22	1.21
II (laminated)	1.75	1.48	1.32	1.41	1.43	1.50	1.47
III (unlaminated)	1.24	1.23	1.13	1.12	1.16	1.23	1.20
30 III (laminated)	1.73	1.49	1.36	1.40	1.46	1.53	1.51
IV (unlaminated)	1.22	1.22	1.11	1.16	1.16	1.22	1.22
IV (laminated)	1.70	1.46	1.33	1.42	1.43	1.54	1.51
V (unlaminated)	1.24	1.20	1.01	1.17	1.10	1.20	1.18

V (laminated)	1.55	1.45	1.15	1.41	1.30	1.46	1.35
---------------	------	------	------	------	------	------	------

Example 5

This example shows a receptor composition of a single multivalent metal salt and a mixture of a non-ionic hydrocarbon surfactant and an anionic hydrocarbon surfactant flood coated onto the porous film with a #4 Meyer rod. The film was dried in air at ambient conditions. After printing the receptor was dry to the touch and had excellent image quality.

10 **Composition V.**

dioctylsulfosuccinate-Na-salt	2.0 wt %
Pluronic 25R4	2.0 wt %
aluminum sulfate	7.5 wt %
ethyl alcohol	25 wt %
15 de-ionized water	63.5 wt % ~

Comparative Example A

This is an example of coating solution that does not contain a multivalent metal salt, just an anionic hydrocarbon surfactant. The solution composition was 20 wt % dioctylsulfosuccinate-Na-salt, 46.5 wt % water, and 46.5 wt % ethanol. It was flood-coated onto the oil-in porous film using a # 4 Meyer rod and dried in air at ambient condition. After printing the receptor was dry to the touch, but all the measured reflected optical densities were poor.

25 The red color bar is composed of a mixture of 100% lay down of magenta and 100% lay down of yellow, in that order. Looking at the individual colors from Comparative Example A, the 100% lay down of magenta has a reflected optical density measurement of .86 and the 100% lay down of yellow has an optical density of .92. However, the optical density of the magenta component in the red color falls to .59 while the optical density of the yellow component slightly increases. The magenta colorant is beneath the yellow colorant in the film and is

visually trapped. The visual effect of this is a washed out yellow orange color that is supposed to be red.

Compare those results with Example 5. Using this invention, all the measured optical densities of the colors are greater because the pigments are closer to each other and to the surface of the film. Another measurable result is the magenta component in red slightly increases while the yellow component slightly decreases. This results from pigments that have mixed better in the porous film so the previous observed color trapping is minimized or eliminated. The porous film utilized by this invention for ink jet imaging resulted in truer colors with higher optical densities while enjoying instantaneous dry time.

In the present invention, the ink carrier fluid is wicked instantly into the film so the surface remains tack free. This enables the film to be picked up for lamination, stacked, or rolled up immediately after printing. The real dry time is when all the volatile components in the ink have evaporated out of the membrane. This may take up to a half hour or more depending on temperature and humidity.

Example 6

This example describes a continuous coating process for the pigment/fluid management solution composition as applied to a roll 200 meters long of oil-in-PP porous film laminated to a paper liner using 3M's adhesive disclosed in EPO Pat. Ilub. EP 0 570 515 B I (Steelman et al.), as above. A composition similar to Example 3 was used except the aluminum sulfate was 4.63 wt %, the dioctylsulfosuccinate-Na-salt was 7.0 wt %, and the water was 62.37 wt %. The solution was fed to a slot knife by a gear pump at a rate where the solution flood coated the porous film but not in excess. The coated web was fed into a forced air oven at 4.6 meters/min maintained at 100 °C and wound on a core. The receptor material was imaged on a Encad Nova Jet III with 3M pigmented ink, Encad "GO" pigmented ink, and Graphic Utilities pigmented ink where it was found that all of the images, regardless of which ink was used in printing, were dry to touch, waterfast, smudge and smear resistant immediately out of the printer, and had excellent reflective image quality with and without an overlamine.

Example 7

This example shows a receptor composition consisting of a multivalent metal salt and a mixture of two nonionic surfactants and one anionic surfactant flood-coated onto the oil-in PP porous film and wiped with a #4 Meyer rod. The film was dried in air at ambient conditions. Immediately after printing the image was dry to the touch, the colors did not smear when rubbed, and the image quality was excellent because the dispersed pigment in the ink was rapidly agglomerated and captured below the surface as it entered the porous film.

Composition VII

Aluminum sulfate	6.0 wt %
Surfynol 104	2.0 wt %
Silwet L-7607	1.0 wt %
Dioctylsulfosuccinate-Na-salt	7.0 wt %
ethyl alcohol	25.0 wt %
de-ionized water	59.0 wt %

Comparative Example B

The same solution as in Example 7 was prepared except no metal salt was added. The solution was flood-coated onto an oil-in PP porous film and wiped with a Meyer rod and dried. After printing, the image was dry to the touch, but the color densities were dull and diffuse because the dispersed pigment in the ink was not rapidly destabilized and agglomerated.

Example 8

A commercially available hydrophilic nylon membrane from Gelman Sciences, Ann Arbor, MI, called Nyloflo 0.2 μm was flood-coated with a 5.25 wt. % aluminum sulfate solution in water, wiped with a #4 Meyer rod and dried at ambient conditions. During printing, the image dried instantly and the color densities were high.

Comparative Example C

The same nylon membrane used in Example 8 without the metal salt coating was imaged. The image dried instantly during printing, but the colors were dull and diffuse because the dispersed pigment in the ink was not destabilized and agglomerated.

Example 9

A commercially available hydrophobic polysulfone 0.45 μm membrane from Gelman Sciences was coated with a 5.25 wt. % aluminum sulfate, 9.0 wt. % dioctylsodium sulfosuccinate, 25.0 wt. % ethanol, 60.75 wt % de-ionized water solution, wiped with a # 4 Meyer rod, and dried at ambient conditions. During printing, the image dried instantly and the color densities were high.

Comparative Example D

The same membrane used in Example 9 was flood-coated with a 6.0 wt % solution of dioctylsodium sulfosuccinate solution without the metal salt, wiped with a # 4 Meyer rod, and dried at ambient conditions, and imaged. The image dried instantly during printing, but the colors were dull and diffuse.

Example 10

A commercially available hydrophilic ethylene vinyl alcohol copolymer (EVAL) 0.5 μm membrane from 3M was flood-coated with 5.25 wt % aluminum sulfate in water, wiped with a # 4 Meyer rod, and dried at ambient conditions. During printing, the image dried instantly and the color densities were high.

Comparative Example E

The same membrane used in Example 10 without a metal salt coating was used for inkjet printing. The imaged area dried instantly, but the colors were dull and diffuse because the dispersed pigment in the ink travel through the membrane and was not destabilized and agglomerated.

Comparative Example F

This example shows a receptor coating consisting of the pigment management system: 5.25 wt % aluminum sulfate; 30 wt % ethanol; and 64.75 wt % de-ionized water, coated on the hydrophobic oil-in PP porous film. No fluid management system was used to wick away the inkjet ink carrier fluids. The solution was flood-coated, wiped with a # 4 Meyer rod, and dried at ambient conditions. During and after printing, the image dried very slowly, was distorted, and had unacceptable quality because the pigmented inks pooled on the surface of the membrane, did not soak in, and coalesced as well.

Example-11:

This example describes one method of preparation of the functionalized silica, a SiO_2 -*i*-pr- NH_2 -HF system:

To 100g (15% solid, 15g, 0.245 mole) of a colloidal silica sol (Nalco 2326, average particle size - 4 nm) in a three-neck flask fitted with a reflux condenser and a mechanical stirrer was added 45g (0.75 mole) isopropylamine under stirring at room temperature. To the mixture was dropwise added, at room temperature, after dilution with 100g de-ionized water, 30g (50% in water, 15g, 0.75 mole) hydrofluoric acid under stirring. The system was somewhat exothermic and during the addition of acid 50g de-ionized water was added under stirring to disperse the formed gel. After the addition of all the acid, the system was heated to vigorous refluxing of water under mechanical stirring of about 150-200 rpm. After 3-4 days a white colloidal system resulted.

The material in combination with a binder copolymer of n-vinylpyrrolidone and dimethylaminoethylmethacrylate (copolymer-958, from ISP) was coated onto a polyvinyl chloride (PVC) base and dried at 100°C for 4 mins. The dry coating was subjected to SEM analysis which shows a highly microporous surface. The colloidal material in very dilute suspension was subjected to TEM analysis which shows an agglomerated morphology. X-ray powder diffraction shows the material to be microcrystalline morphology. BET specific surface area measurement shows

that the sample has a SSA of about 210-250m²/g with a pore volume of 0.12cc/g and a pore diameter of 110-140Å. The surface shows a rate of absorption of ink (water) in the range of 25-50 ml/m²/sec.

5 **Example-12:**

 This example describes another method of preparation of the functionalized silica. To 40g (15% solid, 6g, 0.10 mole) of a colloidal silica sol (Nalco 2326, average particle size ~ 4 nm) in a three-neck flask fitted with a reflux condenser and a mechanical stirrer was added 10g (0.08 mole) quinuclidine under stirring at
10 room temperature. To the mixture was dropwise added, at room temperature, after dilution with 110g de-ionized water, 8g (50% in water, 4g, 0.20 mole) hydrofluoric acid under stirring. After the addition of all the acid, the system was heated to vigorous refluxing of water under mechanical stirring of about 100-200 rpm for 18
15 hr. After this period of time an opaque colloidal dispersion resulted.

Example-13:

 This example shows the functionalized silica coating composition flood-coated onto the microporous oil-in-PP using a Meyer rod #4 and drying the film in
20 air or by brief heating using a heat gun. The composition was also coated using machine coating, as described in Example 6.

Composition-13:

 Fluorinated microporous silica 2-3%

25 Binder Polymer (Cop-958)' 0.5-0.7%

 Dioctylsulfosuccinate-Na salt, DOS' (Cyanamid) 1.5-2.0%

 Isopropyl Alcohol 80-85%

 DI-water 10-12%

30 *NVP/DMAEMA (20/80)

Example-14:

This example shows another coating composition coated onto the microporous oil-in-pp. The composition was flood-coated onto the oil-in-pp using a Meyer bar #4 and the film was dried in air or optionally using brief heating with heat gun. The dry film was imaged in various wide-format commercial printers.

5

Composition-14(a):

Fluorinated microporous silica	2-3%
Binder Polymer (Cop-958)*	0.5-0.7%
10 Fluorochemical surfactant (Zonyl-FSO, Dupont)	0.5-1.0%
Diocylsulfosuccinate-Na salt, Dos ³ (Cyanamid)	0.5-1.0%
Isopropyl Alcohol	30-40%
DI-water	50-55%

15 * NVP/DMAEMA (20/80)

Composition 14(b) & (c):

20 These compositions are the same as composition 14(a) except that for 14(b) fluorochemical surfactant FC- I 70C and for 14(c) silicon-based surfactant Silwet L-7607 were used.

Example-15:

25 This example shows another coating composition coated onto the microporous oil-in-pp. The composition was flood-coated onto the oil-in-pp using a Meyer bar #4 and the film was dried in air or optionally using brief heating with heat gun. The dry film was imaged in various wide-format commercial printers.

30 **Composition- 15:**

Fluorinated microporous silica	2-3%
Binder Polymer (Cop-958)*	0.5-0.7%

Fluorochemical surfactant (Zonyl-FSO, Dupont)	0.5-1.0%
Isopropyl Alcohol	30-40%
DI-water	50-55%

5 *NVP/DMAEMA (20/80)

Example-16:

10 (a) This example shows the image density on the developed receptor coated with composition- 13 (example- 13) of different colors imaged in an Encad-Novajet-III wide-format printer - the final image being laminated and unlaminated.

TABLE 2
COLOR DENSITY MEASUREMENTS

15

Film	Color Density						
	Black	Cyan	Magenta	Yellow	Red	Green	Blue
Comp-13 (unlaminated)*,®	1.30	1.04	0.91	1.17	1.02	1.05	0.84
20 Comp-13 (unlaminated)*,ª	1.22	1.15	1.10	1.19	1.11	1.15	1.11
Comp-13 (laminated)*,ª	1.77	1.32	1.32	1.49	1.37	1.40	1.35
Comp-13 (unlaminated)*,§	1.28	1.21	1.10	1.23	1.20	1.19	1.16
25 Comp-13 (laminated)*,§	1.57	1.38	1.50	1.57	1.62	1.50	1.45

* using silica from example-11, ª using silica from example-12

® using Rev- I ink set, § using Rev- I /N-magenta ink set

ª using modified black/N magenta

30

(b) This example shows the image density on the developed receptor coated with composition-14(a) (Example-14) of different colors imaged in an

EnCad-Novajet-III wide-format printer - the final image being laminated and unlaminated.

TABLE 3
COLOR DENSITY MEASUREMENTS

Film	Color Density						
	Black	Cyan	Magenta	Yellow	Red	Green	Blue
Comp-14(a) (unlaminated)*, ^Δ	1.21	1.19	1.09	1.29	1.26	1.29	1.18
Comp-14(a) (laminated)*, ^Δ	1.74	1.41	1.33	1.66	1.57	1.59	1.51

(c) These examples show the image densities on the developed receptors coated with composition-14(b) and 14(c) (Example-14) of different colors imaged in an Encad-Novajet-III wide-format printer - the final image being laminated and unlaminated.

TABLE 4
COLOR DENSITY MEASUREMENTS

Film	Color Density						
	Black	Cyan	Magenta	Yellow	Red	Green	Blue
Comp-14(b) (unlaminated)*, ^Δ	1.23	1.10	1.05	1.24	1.10	1.19	1.13
Comp-14(b) (laminated)*, ^Δ	1.71	1.32	1.31	1.58	1.55	1.56	1.45
Comp-14(c) (unlaminated)*, ^Δ	1.27	1.13	1.08	1.21	1.17	1.18	1.13
Comp-14(c) (laminated)*, ^Δ	1.71	1.39	1.39	1.62	1.50	1.45	1.42

(d) This example shows the image density on the developed receptor coated with composition- 15 (Example- 15) of different colors imaged in an Encad-Novajet-III wide-format printer - the final image being laminated and unlaminated.

TABLE 5
COLOR DENSITY MEASUREMENTS

Film	Color Density						
	Black	Cyan	Magenta	Yellow	Red	Green	Blue
Comp-15 (unlaminated)*, ^Δ	1.25	1.12	1.04	1.23	1.16	1.21	1.13
Comp-15 (laminated)*, ^Δ	1.70	1.30	1.27	1.47	1.44	1.50	1.41

Example-17:

This example shows a comparison of the image densities in Example- I 6(a) to those in the receptors obtained by replacing the microporous silica with the commercially available ones.

TABLE 6
COLOR DENSITY MEASUREMENTS

Film	Color Density						
	Black	Cyan	Magenta	Yellow	Red	Green	Blue
Comp-13 (unlaminated)*, [⊗]	1.30	1.04	0.91	1.17	1.02	1.05	0.84
Comp-13 (unlaminated)*, ^Δ	1.22	1.15	1.10	1.19	1.11	1.15	1.11
Comp-13 (laminated)*, ^Δ	1.77	1.32	1.32	1.49	1.37	1.40	1.35
Comp-13 (unlaminated)*, [§]	1.28	1.21	1.10	1.23	1.20	1.19	1.16
Comp-13 (laminated)*, ^Δ	1.57	1.38	1.50	1.57	1.62	1.50	1.45
Ludox* silica	0.88	0.77	0.76	1.00	0.62	1.04	0.73
Spherical* silica	0.87	0.79	0.83	0.95	0.64	1.05	0.78

* using silica from example-11, ^Δ using silica from example-12

[⊗] using Rev- I ink set, [§] using Rev- I/N-magenta ink set

& using modified black/N magenta

*Ludox silica commercially available from DuPont of Wilmington, Delaware, USA

*Spherical silica commercially available from Nissan Chemicals Inds. Ltd. of Tokyo, Japan

Example-18:

This example shows the compositions, consisting of fluorinated silica of Example- 11, developed for a single-layer coating onto various substrates e.g., polyvinylchloride, polyester, microvoided polyester, paper, polycarbonate etc. The compositions were coated onto various substrates using a knife-coater at various wet % of solids typically 18-22%. The coated films were dried for 3-4 mins. in an air-forced oven operating at 105°C.

(a) Composition 18(a):

10	Fluorinated microporous silica	60%
	Copolymer-958'	39%
	Fluorochemical surfactant@	0.5-1%

(b) Composition 18(b):

15	Fluorinated microporous silica	58%
	Copolymer-958'	38%
	Snowtax#	3%
	Fluorochemical surfactant@	0.5-1.0%

'NVP/DMAEMA (from ISP);

20 #Spherical silica (from Nissan Chemical);

@Zonyl FSO (from E.I.Dupont)

Example-19:

25 This example shows the image density of the coated PVC with composition 18(a) and 18(b) in the wide-format Encad Novajet inkjet printer operating with both dye- and pigment-based inks.

TABLE 7**COLOR DENSITY MEASUREMENTS**

30	Comp.	Ink type	Color Density						
			Black	Cyan	Magenta	Yellow	Red	Green	Blue
	18(b)	Pigment*	1.20	1.22	0.85	0.84	0.85	1.12	1.01

18(a)	Dye ^a	1.53	1.54	1.23	1.56	1.35	1.50	1.41
18(a)	Dye ^b	2.07	1.97	1.35	1.90	1.70	1.90	1.76

no overlamine, ^a overlamine

The invention is not limited to the above embodiments. As seen in the last Example, it is possible to employ the silica agglomerate pigment management system successfully with respect to dye-based inks, recognizing that such inks will continue to have a place in specific markets even after preferred pigment-based inks become dominant in the image graphics industry. Others skilled in the art will appreciate other possible combinations of pigment management systems and fluid management systems will be feasible for a variety of inks and media once having been exposed to the scope of the present invention. The claims follow.

What is claimed is:

1. An inkjet receptor medium, comprising:
a porous substrate having a fluid management system and having a pigment
5 management system in contact with surfaces of pores of the substrate therein.
2. The medium of Claim 1, wherein the pigment management system
comprises functionalized particulates within the pores that chemically interact with
10 pigment particles through interaction with dispersants engaged with the pigment
particles.
3. The medium of Claim 1, wherein the pigment management system
comprises a functionalized coating along the surfaces that chemically interact with
15 pigment particles through interaction with dispersants engaged with the pigment
particles.
4. The medium of Claim 3, wherein the functionalized coating
comprises a multivalent metal salt that interacts with dispersants to agglomerate
20 pigment particles as an ink containing the pigment particles passes through pores.
5. The medium of Claim 2, wherein the functionalized particulates
comprise fluorinated silica agglomerates that interact with dispersant to
25 agglomerate pigment particles as an ink containing the pigment particles passes
through pores.
6. The medium of any of Claims 1-5, wherein the fluid management
system comprises porosity itself of the porous substrate.

30

7. The medium according to any of Claims 1-5, wherein the fluid management system comprises a surfactant that carries away an ink passing through the substrate except for pigment particles in the ink.

5 8. The medium according to any of Claims 1-7, wherein the microporous substrate comprises a polypropylene film co-extruded with a mineral oil followed by bi-axial stretching under thermal conditions.

9. A method of making an inkjet receptor medium, comprising the
10 steps of:
(a) preparing a pigment management system; and
(b) imbibing the pigment management system into pores of a porous substrate, wherein the pigment management system is selected from the group consisting of functionalized particulates within the pores that chemically interact
15 with the pigment particles through interaction with dispersants surrounding the pigment particles and a functionalized coating along the surfaces that chemically interact with pigment particles through interaction with dispersants surrounding the pigment particles.

20 10. The method according to Claim 9, further comprising the step (c) imbibing a fluid management system into the pores of the porous substrate.

11. A method of using an inkjet receptor medium, comprising the steps
25 of:

(a) placing an inkjet receptor medium of any of Claims 1-8 in an inkjet printer; and
(b) printing an image on the medium using inkjet ink, wherein
30 pigment particles are agglomerated using the pigment management system and fluid is passed through pores of the porous substrate using the fluid management system.

INTERNATIONAL SEARCH REPORT

Inte. onal Application No

PCT/US 98/14259

A. CLASSIFICATION OF SUBJECT MATTER

IPC 6 B41M5/00

According to International Patent Classification(IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 6 B41M

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	WO 95 28285 A (ILFORD AG) 26 October 1995 see claims 1,4,7,8,23,36; examples 1,3,5-7 see page 8, line 13 - line 22 see page 10, line 14 - line 20 see page 13, line 13 - line 17 see page 15, line 13 - page 16, line 16 ---	1-4,6,7, 9-11
X	US 5 084 340 A (W.A.LIGHT) 28 January 1992 cited in the application see column 3, line 4 - line 34 see column 6, line 58 - column 7, line 53 see claims 1-3,14,15 --- -/--	1-4,6,7, 9-11

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents :

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier document but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

"8" document member of the same patent family

Date of the actual completion of the international search

24 September 1998

Date of mailing of the international search report

06/10/1998

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Bacon, A

INTERNATIONAL SEARCH REPORT

International Application No

PCT/US 98/14259

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	<p>US 4 954 395 A (K.HASEGAWA ET AL.) 4 September 1990 cited in the application see column 2, line 41 - column 3, line 3 see column 4, line 65 - column 5, line 6 see column 6, line 3 - line 28 see column 8, line 33 - column 9, line 3 see claims 1,7,13,19,25 -----</p>	<p>1-4,6,7, 9-11</p>